



Product overview

Composition® is a durable, high-performance acoustic wallcovering designed as a paint or wallpaper alternative. Made from 100% polyester fibre, Composition has a velvety soft hook-and-loop receptive pile, and pinnable self-healing surface.

Sustainable material

- Carbon neutral product
- Zero carbon manufacturing
- Recycled content
 - >60% recycled material
- Low VOC and CDPH compliant
 - <0.0035 mg/m³ (7 days)
- Zero waste manufacturing initiative
- Sustainable supply chain and anti-modern slavery

Environmental certifications

- EPD – compliant with ISO 14025 and ISO 15804
- Declare – Red List free (third party verified)
- ISO 14001 Certified Environmental Management
- Health Product Declaration
- CDPH Standard



Certifying your green building

Autex Acoustics products meet criteria for WELL, LEED, Green Star, and BREEAM building rating systems, helping you achieve certification for your project. For support and guidance on available rating system points please visit www.autexglobal.com, or speak with your Autex Acoustics account manager.

Specification

(Wall) treatment shall be Autex Acoustics Composition® made from non-woven needle-punched polyester containing not less than 60% recycled material as manufactured by Autex www.autexglobal.com

Install as per Autex Acoustics recommendations. If Composition is to be specified for use other than as a wallcovering, please seek guidance from your account manager.

Roll 10 - 12 mm (nom.) depth, colour (L), sound absorption: Class D, NRC 0.40, Fire ratings: ISO 9705: Classification: Group 1-S, AS ISO 9705 – 2003: Classification: Group 1, BS EN 13501-1:2018: B - s1, d0.



Product specifications

Product name	Composition®
Composition	100% polyester fibre (PET)
Roll dimensions	1.22 m x 25 m
Tolerance	(+ 5 mm) (+ 10 mm)
Thickness	10 - 12 mm
Weight	1680 gsm

Installation

Install as per Autex Acoustics recommendations. Install instructions are included in each pack or available on the website. If Composition is to be specified for use other than as a wallcovering, please seek guidance from your account manager.

Thermal performance

10 - 12 mm R0.22 (@15°C)

Acoustic performance

Composition is specifically designed to reduce and control reverberated noise and echo in building interiors

Product specifications

Fire ratings

Composition has been evaluated using the following test methods:

ISO 9705: 1993

Classification: Group 1-S

Smoke production rate:

<5.0m²/s

As required by NZBC C/VM2

AS ISO 9705 - 2003

Classification: Group 1

(SMOGR_{arc}): <100m²/s²

Assessed using methodology AS ISO 9705:2003 in accordance with AS 5637:2015, as required by BCA Specification C110-4 FI 4894 and FAR 4055

BS EN 13501-1:2018

Classification: B-s1,d0

Tested using BS EN ISO 11925-2:2020 and BS EN 13823:2020 and classified in accordance with BS EN 13501-1:2018, as required by BS EN 15102:2007 + A1:2011. EUI-21-000135-C

ASTM E84 - 14

Class A, FS:5 - SD:25

Report RJ3297-9R1

Water vapour sorption

ASTM C1104 / C1104M-13a

Test conditions: 49°C, 95%RH

Water vapour absorbed and adsorped after

4 days: 0.4% by weight

Impact resistance

ISO 7892:1988

Hard body impact

There is no surface damage or penetration to Composition when subjected to hard body impacts. When adhered to 10 mm plasterboard, the system can resist a 9 joule impact.

This is equivalent to the impact of a 0.5 kg object dropped from a 2 m height. A small indentation might be observed when subjected to an impact equivalent to the impact of a 0.5 kg object dropped from a 0.5 m height.

Soft body impact

There is no surface damage or penetration to Composition when subjected to soft body impacts. When adhered to 10 mm plasterboard, the system can resist a 70 joule impact. This is equivalent to the impact of a 50 kg object dropped from a 150 mm height.

Microbial resistance

ASTM G21-15

Growth rating: 0 (No growth)

Composition does not promote the growth of moulds and mildew.

Colour fastness to light

Composition is suitable for indoor use only. Light fastness is dependent on use and exposure.

Composition has been evaluated to the following standard:

ISO 105-B02:2014

Rating: 6 (Highest = 7)

Colour fastness to rubbing

ISO 105-X12:2016

Dry rating: 4-5 (Highest = 5)

Wet rating: 4-5 (Highest = 5)

Moisture absorption

Polyester fibre when exposed to an atmosphere of 50°C at 90% relative humidity for four days showed moisture absorption of less than 0.03% by weight. Polyester is not affected by moisture and will not rot or deteriorate in intended use situations.

Fabric care

Blot spills from fabric quickly. Wipe with a damp cloth. Avoid rubbing and excessive amounts of water as this will affect the finish. Use carpet or upholstery shampoo as directed. Blot with a clean dry cloth after each application of solution.

Custom printed Composition requires the services of a specialist cleaning company. Refer to the Composition Care and Maintenance Guide for more information.

Pattern repeat

Non-woven. No pattern repeat but product has directional grain. Product may vary from samples and batch to batch due to fibre blending and lay-up, which is an inherent feature of this product.

Service

For further information about Composition or any other Autex Acoustics product, please contact your account manager or visit our website.



Acoustic performance


Composition is specifically designed to reduce and control reverberated noise and echo in building interiors.

Minimum Noise Reduction Coefficient 0.40

Frequency (Hz)	125	250	500	1000	2000	4000	NRC
● 10 - 12 mm Composition	0.05	0.10	0.25	0.55	0.80	0.95	0.40

Table presents the practical sound absorption coefficients as according to ISO 11654. Graph presents third octave sound absorption coefficients (according to ISO 354 measurement of sound absorption in a reverberation room.) The NRC rating is determined as the arithmetic average of the absorption coefficients measured by one-third octave bands centred on 250 Hz, 500 Hz, 1000 Hz and 2000 Hz. and rounded to the nearest 0.05.

Sound Absorption Coefficients according to ISO 354.
University of Auckland Testing Service
Composition 10 - 12 mm - Test No. T0814-2b.



Light reflectance values by colour

Composition is suitable for indoor use only. LRVs were measured in accordance with BS 8493:2008+A1:2010

Civic	57	Koala	12
Citrus	49	Avocado	11
Myst	42	Sage	9
Sanz	36	Emerald	8
Wasabi	33	Sapphire	8
Lime	29	Atlantis	8
Azure	24	Blazing Red	8
Silver	23	Raspberry	8
Jade	22	Vintage	6
Porcelain	22	Chilli Red	5
Calypso	13	Cinder	5
Fawn	20	Bark	5
Clay	20	Octane	5
Granny Smith	20	Phantom	4
Stone wash	19	Theatre	3
Simba	18	Stately	3
Brilliant Orange	15	Charcoal	3
Spearmint	13	Lightsout	3
Calypso	13	Ink	3
Electric Blue	12	Noir	1

● Autex Industries Ltd

702-718 Rosebank Rd
Private Bag 19988
Avondale 1746, Auckland
New Zealand
Freephone 0800 428 839
Phone +64 9 828 9179
Fax +64 9 828 5810

● Autex Australia Pty Ltd

166 Bamfield Road
PO Box 5099
West Heidelberg, Melbourne
VIC 3081, Australia
Freephone 1800 678 160
Phone +61 3 9457 6700
Fax +61 3 9457 1020

● Autex Acoustics Ltd

Unit J4, Lowfields Way,
Lowfields Business Park,
Elland, West Yorkshire
Hx5 9Da
United Kingdom
Phone +44 0 1422418899

● Autex Acoustics LLC

1630 Dan Kipper Dr,
Riverside, CA 92507
United States of America
Phone +1 424 203 1813

An ISO 9001, ISO 14001 and ISO 45001 certified company. The brand names and logos mentioned herein are registered or unregistered trademarks either owned or used under license by Autex Industries Limited or other members of the Autex Group. The contents of this document are protected by Copyright 2021 Autex Industries Ltd. All Rights Reserved. It is the user's responsibility to determine if the product and information presented in this document is suitable for the intended application by engaging a suitably qualified consultant. The information contained in this document is correct to the best of our knowledge at the date of its publication. To verify that this document is the most current publication please check our website or contact your Autex account manager.