

Quietspace® Panel

Data Sheet

Product overview

Quietspace® Panel is a high-performance acoustic treatment engineered to absorb a minimum of 85% of the sound energy it meets. Made from 100% polyester fibre, Quietspace Panel has a hard, compressed face and cushioned backing, available in 25 mm, 50 mm, 75 mm, and 100 mm thicknesses.

Sustainable material

- · Carbon neutral product
- · Zero carbon manufacturing
- · Recycled content
 - >60% recycled material
- Low VOC and CDPH compliant
 - <0.035 mg/m3 (7 days)
- Zero waste manufacturing initiative
- Sustainable supply chain and anti-modern slavery

Environmental certifications

- EPD compliant with ISO 14025 and ISO 15804
- Declare Red List free (third party verified)
- ISO 14001 Certified Environmental Management
- · Health Product Declaration
- CDPH Standard











Certifying your green building

Autex Acoustics products meet criteria for WELL, LEED, Green Star, and BREEAM building rating systems, helping you achieve certification for your project. For support and guidance on available rating system points please visit www.autexglobal.com, or speak with your Autex Acoustics account manager.

Specification

(Wall/Ceiling) treatment shall be Quietspace® Panel made from thermally bonded polyester containing no less than 45% recycled material as manufactured by Autex www.autexglobal.com

Panel 1200 mm x 2400 mm x (_)mm nom depth, sound absorption: 25 mm: Class C, NRC 0.85, 50 mm: Class A, NRC 1.00. Fire rating fullk range of thicknesses: ISO9705:

Classification: Group 1-S, AS ISO 9705 – 2003: Group 1, 25 mm BS EN 13501-1:2018: B - s2, d2

Install as per Autex Acoustics recommendations. If Quietspace Panel is to be specified for use other than as a ceiling or wallcovering please seek guidance from your specification manager.



Product specifications

Product name Quietspace® Panel
Composition 100% polyester fibre (PET)
Panel dimensions 1200 mm x 2400 mm
Tolerance (+ 5 mm) x (+ 10 mm)

Thickness	25 mm	50 mm	75 mm	100 mm	
Tolerance	(+/- 6%)	(+/- 6%)	(+/- 6%)	(+/- 6%)	
Weight	2300 gsm	3800 gsm	4050 gsm	4300 gsm	

Installation

Install as per Autex Acoustics recommendations. Install instructions are included in each pack, or available on the website. If Quietspace Panel is to be specified for use other than as a wallcovering, please seek guidance from your specification manager. In situations where product is being installed near fire protection systems (e.g. sprinklers or fire alarms) relevant building codes, standards and design rules must be adhered to.

Please consult the project engineer and relevant expert such as a fire protection engineer.

Light reflectance

White Quietspace Panel is suitable for indoor use only and has a light reflectance value of 83 (measured in accordance with BS 8493:2008+A1:2010).

Thermal performance

25 mm: R0.6 (@23°C) 50 mm: R1.4 (@23°C) 75 mm: R1.9 (@23°C) 100 mm: R2.4 (@23°C)

DI III

Product specifications

Fire ratings

Quietspace® Panel has been evaluated using the following test methods:

ISO 9705: 1993

Classification: Group 1-S Smoke production rate: <5.0m2/s As required by NZBC C/VM2

AS ISO 9705 - 2003

Classification: Group 1 (SMOGRArc): <100m2/s2

Assessed using methodology AS ISO 9705:2003 in accordance with AS 56371:2015, as required by BCA Specification C1:10-4 F1 4871 FAR 4055

BS EN 13501-1:2018

(25 mm Quietspace® Panel)

Wall applications

Classification: B-s2,d2

Tested using BS EN ISO 11925-22020 and BS EN 13823-2020 and classified in accordance with BS EN 13501-1:2018, as required by BS EN 15102:2007 + A1:2011.

EUI-21-000135-E-A

Ceiling applications Classification: B-s2,d2

Tested using BS EN ISO 11925-22020 and BS EN 13823-2020 and classified in accordance with BS EN 13501-12018, as required by BS EN 13964-2014 EUI-21-000135-E-B

ASTM E84 - 14

(1" Quietspace® Panel) Class A, FS:0 - SD:10

Water vapour sorption

ASTM C1104 / C1104M-13a Test conditions: 49°C, 95%RH Water vapour absorbed and adsorped after 4 days: 0.4% by weight.

Pattern repeat

Non-woven. No pattern repeat but product has directional grain. Product may vary from samples and batch to batch due to fibre blending and lay-up, which is an inherent feature of this product.

Impact resistance ISO 7892:1988

Hard body impact

There is no surface damage or penetration to Quietspace Panel when subjected to hard body impacts. A small indentation might be observed when subjected to an impact equivalent to the impact of a 0.5 kg object dropped from a 0.5 m height. When adhered to 10 mm plasterboard, the system can resist a 14 joule impact, and no further indentations are observed. This is equivalent to the impact of a 0.5 kg object dropped from a 3 m height.

Soft body impact

There is no surface damage or penetration to Quietspace Panel when subjected to soft body impacts. When adhered to 10 mm plasterboard, the system can resist a 120 joule impact. This is equivalent to the impact of a 50 kg object dropped from a 250 mm height.

Microbial resistance

ASTM G21-15 Growth rating: 0 (No growth) Quietspace Panel does not promote the growth of moulds and mildew.

Fabric care

Blot spills from fabric quickly. Wipe with a damp cloth. Avoid rubbing and excessive amounts of water as this will affect the finish. Use carpet or upholstery shampoo as directed. Blot with a clean dry cloth after each application of solution. Custom printed Quietspace Panel requires the services of a specialist cleaning company. Refer to the Quietspace Panel Care and Maintenance Guide for more information.

Service

For further information about Quietspace Panel or any other Autex Acoustics product, please contact your account manager or visit our website.



Acoustic performance


Quietspace Panel is specifically designed to reduce and control reverberated noise and echo in building interiors. Minimum Noise Reduction Coefficient 0.85

	Frequency (Hz)	125	250	500	1000	2000	4000	NRC	
•	25 mm	0.15	0.45	0.85	1.00	1.00	0.95	0.85	
•	50 mm	0.30	0.75	1.10	1.10	1.05	1.00	1.00	
•	75 mm	0.50	0.90	1.05	1.05	0.95	0.90	1.00	
•	100 mm	0.65	1.00	1.05	1.00	0.95	0.90	1.00	

Table presents the practical sound absorption coefficients as according to ISO 11654. Graph presents third octave sound absorption coefficients (according to ISO 354 measurement of sound absorption in a reverberation room). The NRC rating is determined as the arithmetic average of the absorption coefficients measured by one-third octave bands centred on 250 Hz, 500 Hz, 1000 Hz and 2000 Hz and rounded to the nearest 0.05.

Absorption Coefficient according to ISO 354 University of Auckland Testing Service

Quietspace Panel 25 mm - test no. T0712-18 Quietspace Panel 50 mm - test no. T1228-8 Quietspace Panel 75 mm - test no. T1905-4 Quietspace Panel 100 mm - test no. T1905-5



Autex Industries Ltd

702-718 Rosebank Rd Private Bag 19988 Avondale 1746, Auckland New Zealand Freephone 0800 428 839 Phone +64 9 828 9179 Fax +64 9 828 5810

Autex Australia Pty Ltd

166 Bamfield Road PO Box 5099 West Heidelberg, Melbourne VIC 3081, Australia Freephone 1800 678 160 Phone +61 3 9457 6700 Fax +61 3 9457 1020

Autex Acoustics Ltd

Unit J4, Lowfields Way, Lowfields Business Park, Elland, West Yorkshire Hx5 9Da United Kingdom Phone +44 0 1422418899

Autex Acoustics LLC

1630 Dan Kipper Dr, Riverside, CA 92507 United States of America Phone +1 424 203 1813